

ChemGrout MSG

Cementitious, Non-Shrink, Medium Strength Grout

Description: - ChemGrout MSG is a cement-based flow able, Non-Shrink medium strength cementitious grout. ChemGrout MSG is supplied as ready to use dry powder requiring only addition of clean water as per guideline of water powder ratio. It is non-shrink high strength flow able grout.

Characteristic Parameters

It conforms to specification prescribed in BS: 1881-1983, BS: 4551-1998

Test Parameters	Specification
Appearance	Free flowing cementitious powder
Compressive strength, Kg/cm ² (70 mm cube) <ul style="list-style-type: none">• 1 Day• 3 Day• 7 Day• 28 Day	150 350 500 600
Flow in cm	20 -25
Water content per 25 kg bag in Liter <ul style="list-style-type: none">• Flow able consistency• Pourable consistency	4.125 4.000
Setting Time, 27°C, Hrs. <ul style="list-style-type: none">• Initial• Final	4-6 6-8

Note: - Above test results were found under Laboratory conditions. Tested at fluid consistency of 3.75 L of water per 25 kg Grout.

Features/Advantages

- ❖ Non-Shrink, positive expansion.
- ❖ It is free from harmful chlorides.
- ❖ It is easy to mix & apply as only water of a defined quantity must be added at site to readymade grout.
- ❖ Easy flow able.

Applications

- ❖ Machine, Boiler foundations.
- ❖ Bearing Plates.
- ❖ Pumps.
- ❖ Turbines.
- ❖ Anchoring.

Application methodology

Preparation Foundation surface

- ❖ The substrate surface must be free from dust, oil, grease or any loosely adherent material.
- ❖ If the concrete surface is defective or has laitance, it must be cut back to a sound base.
- ❖ Bolt holes and fixing pockets must be blown clean of any dirt or debris.

Pre-soaking

- ❖ Several hours prior to placing, the concrete substrates should be saturated with fresh water.
- ❖ Immediately before grouting takes place any free water should be removed with particular care being taken to blow out all bolt holes and pockets.

Base plate

- ❖ It is essential that this is clean and free from dust, oil, grease or scale.
- ❖ Air pressure relief holes should be provided to allow venting of any isolated high spots.

Levelling shims

- ❖ If these are to be removed after the grout has hardened, they should be treated with a thin layer of grease.

Formwork

- ❖ The formwork should be constructed to be leak-proof. This can be achieved by using foam rubber strip or mastic sealant beneath the constructed formwork and between joints.
- ❖ In some cases it is practical to use a sacrificial semi-dry sand and cement formwork. The formwork should include outlets for pre-soaking.

Mixing and placing

Mixing

- ❖ For best results mix powder with a mechanically heavy duty slow speed (400-500 rpm) drill fitted with a paddle type grout mixer.

Consistency of grout mix

- ❖ The quantity of clean water required to be added to a 25 kg bag to achieve the desired consistency is given below:
 - Pourable: 4.125 liters
 - Flow able: 4.000 liters
- ❖ The selected water content should be accurately measured into the mixer. Then add Slowly 25 kg bag of the Offshore ChemGrout MSG and continuous mixing should take place for 5 minutes.
- ❖ Ensure that the grout has a smooth even consistency.

Placing

- ❖ After achieved the desired consistency Place or poured the mix grout into the prepared foundation.

Cleaning of Tools: Clean all tools and application equipment with water immediately after use. Hardened / cured material can only be mechanically removed.

Health & Safety

- ❖ Before handling product wear suitable protective clothing, gloves, Nose mask, helmet and Goggles.
- ❖ Avoid contact with skin /eyes, and avoid swallowing.
- ❖ Inhalation of dust during mixing should be avoided.
- ❖ If material contacted to skin rinse with plenty of clean water, then cleanse with soap and water.
- ❖ In case of eye contact, wash with plenty of clean water and seek medical advice.

Packing:- 25 kg. Moisture proof bag.

Shelf-Life and Storage Condition: - Shelf life is 12 months if store in a dry and cool place with unopened sealed moisture proof bags. If stored in high temperature and high humidity place, the shelf life may be reduced.

Our Other Products Ranges Are:-

- | | |
|--|---|
| ○ Concrete Admixtures | ○ Concrete Curing Compounds |
| ○ Sealants & Primer | ○ Waterproofing Chemicals |
| ○ Industrial Floorings | ○ Industrial Grouts |
| ○ Concrete Repair Products | ○ Concrete Hardeners |
| ○ Mould Release Agents | ○ Concrete Bonding Agents |
| ○ Adhesive for Tiles, Marbles and Stones | ○ Joint Filler Grouts for Tiles, Marbles and Stones |

Offshore

Important Note:- Offshore Chemox products are confirming standard manufacturing specification and procedure. Offshore Chemox products are given in good faith based on Offshore Chemox current knowledge and experience of the products when properly stored, handled and applied under normal conditions. Offshore Chemox product are confident against defective materials and are sold subject to its standard terms and conditions of sale, copies of which may be obtained on request. Whilst Offshore Chemox endeavors to ensure that any advice, recommendation, specification or information it may give is accurate and correct, it cannot, because it has no direct or continuous control over where or how its products are applied, accept any liability either directly or indirectly arising from the use of its products, whether or not in accordance with any advice, specification, recommendation or information given by it.

OFFSHORE CHEMOX

(AN ISO 9001: 2015 Certified Company)
Plot. No.1032/135 BPCL Petrol Pump
Campus, Gorewada Road, Gittikhadan
Square, Nagpur- 440013 (Maharashtra)
Phone:-07304444499, 8412843399
Email: info.offshorechemox@gmail.com
Web: www.offshorechemox.com



Customized Construction Chemicals